

SurTec® 107

Recyclable Builder, Anticorrosion

Properties

- liquid
- neutral
- free of silicates and surfactants
- recyclable in combination with SurTec 089 via membrane filtration, separator or gravitation oil separator
- suitable for spraying, flooding or continuous lines in combination with SurTec 085
- for spray application together with SurTec 084 or SurTec 086
- emulsifying in combination with SurTec 092 and SurTec 415
- suitable for steel, aluminium, brass etc.
- temporary corrosion resistance on iron and steel

Application

In combination with surfactant boosters, SurTec 107 is suitable for soak-, ultrasonic- and spray processes. Oil, grease and pigments are removable without problems.

make-up values: 2 - 5 %vol SurTec 107
 + 0.1-1 %vol surfactant

temperature: 40-90 °C

application time: 0.5-10 min

Maintenance and Analysis

Analyse and adjust the concentration of SurTec 107 regularly.

Sample Preparation

Take a sample at a homogeneously mixed position. Let it cool down to room temperature. If the sample is turbid, let the turbidity settle down and decant or filter the solution.

SurTec 107 – Analysis by Titration

reagents: 0.1 N hydrochloric or nitric acid
indicator: methyl orange solution (0.04 %)

procedure: 1. Pipette 20 ml bath sample into a 250 ml Erlenmeyer flask.
 2. Dilute to approx. 100 ml with deionised water.
 3. Add 3 drops of indicator.
 4. Titrate with 0.1 N acid from yellow-orange to red.

calculation: consumption in ml · 0.320 = %vol SurTec 107

Technical Specification

(at 20 °C)	Appearance	Density (g/ml)	pH-value (conc.)
SurTec 107	liquid, colourless-orange/red	1.121 (1.11-1.13)	8.2 (7.5-8.9)

Ingredients

- potassium tetraborate
- phosphates
- amines
- salts of organic acids

Stock Keeping

In order to prevent delays in the production process, per 1,000 l bath the following amount should be kept in stock:

SurTec 107 Recyclable Builder 50 kg

Product Safety and Ecology

The safety instructions and the instructions for environmental protection have to be followed in order to avoid hazards for people and environment. The Material Safety Data Sheets (according to European legislation) contain explicit details for this.

The following hazard designations and classifications into water hazard classes (WHC) have to be taken into account:

<i>product</i>	<i>hazard designation</i>	<i>water hazard class</i>
SurTec 107	-	WHC 1

Warranty

We are responsible for our products in the context of the valid legal regulations. The warranty exclusively accesses for the delivered state of a product. Warranties and claims for damages after the subsequent treatment of our products do not exist. For details please consider our [general terms and conditions](#).

Further Information and Contact

In our forum, you can discuss topics of the surface technology:
<http://forum.SurTec.com/>

If you have any questions concerning the process, please contact your local technical department: <http://SurTec.com/International.html>